

# MaxxStrip Application Chart

Application	MaxxStrip Media	Pressure Water	Nozzle Distance		Pressure Air	Nozzle Distance	
1) Graffiti Brick, Concrete	Medium	3,500Psi	6-10 in.		70-110 Psi	1-2ft.	
2) Brass	Fine	2,500-3,500	8-12 in.		50-75 Psi	1-2 ft.	
3) Aluminum	Fine	2,500-3,500	8-12 in.		50-75 Psi	1-2 ft.	
4) Copper	Fine	2,500-3,500	8-12 in.		50-75 Psi	1-2 ft.	
5) Steel	Fine Medium Coarse	3,500-20,000	4-12 in.		80-120 Psi	1-2 ft.	
6) Paint Removal	Medium Coarse	3,500-20,000	4-12 in.		80-120 Psi	1-2 ft.	
7) Paint Oxidation Removal	fine	3,000-3,500	8-12 in.		60-80 Psi	1 ft.	
8) Light Rust Removal	Medium	3,500-5,000	6-8 in.		80-110 Psi	1 ft.	
9) Heavy Rust Removal	Medium Coarse	5,000-20,000	2-6 in.		100-120Psi	1 ft.	
10) Marble Stone	Fine	2,500-3,000	8-12 in.		40-60 Psi	1-2 ft.	
11) Granite Stone	Fine	2,500-4,000	8-12 in.		50-75 Psi	1-2 ft.	
12) Sandstone	Fine	2,000-3,000	8-12 in.		40-60 Psi	1.5-2.5 ft.	
13) Brick (soft)	Fine	2,000-3,000	8-12 in.		40-60 Psi	1-2 ft.	
14) Brick (hard)	Medium Fine	3,000-3,500	6-12 in.		50-80 Psi	1-2 ft.	
<b>NOTE: APPROXIMATE VALUES</b>						11/7/2002	

# MaxxStrip Application Chart

Application	MaxxStrip Media	Pressure Water	Nozzle Distance		Pressure Air	Nozzle Distance	
15) Oily Concrete	Medium	3,500-4,000	4-8 in.		80-100 Psi	1-2 ft.	
16) New Concrete Prep for coatings	medium Coarse	3,500-10,000	4-8 in.		80-110 Psi	8-12 in.	
17) Fiberglass	Fine Medium	3,000-5,000	6-8 in.		60-80 Psi	1-2 ft.	
18) Cast Molds Cast Iron - Steel	Fine Medium	3,500-5,000	6-8 in.		75-110 Psi	8-15 in.	
19) Cast molds Fiberglass	Fine	3,000-3,500	8-12 in.		50-75 Psi	1-2 ft.	
20) Auotmobile Paint Removal	Medium	3,500-5,000	6-8 in.		80-110 Psi	1-2 ft.	
21) Electric Motor Stators	Fine Medium				75-100 Psi	1-2 ft.	
22) Automotive Parts Cleaning	Fine Medium	3,000-4,000	8-12 in.		40-70 Psi	1-2 ft.	
23) Stainless Steel	Fine Medium	3,500-5,000	8-12 in.		60-100 Psi	8-15 in.	
24) Weld Inspec.	Medium	3,000-5,000	6-10 in.		75-110 Psi	8-15 in.	

**NOTE: APPROXIMATE VALUES ONLY**  
**All Values subject to operator speed and technique**

11/7/2002